

RonaScreed 1 Day Overlay Rapid Drying Screed

Cement replacement system for rapid drying screeds



FEATURES

- rapid hardening—light foot traffic in 6 hours
- rapid drying—can receive floor coverings such as tiles, vinyl, carpet, and epoxy resin after 1 day @ 75mm thick
- apply as bonded, unbonded or floating screed
- can be applied as thin as 25mm
- rapid strength development
- compressive strength >40N/mm² after 28 days
- compatible with underfloor heating systems

Description

RonaScreed 1 Day Overlay Rapid Dry Screed is a cement replacement for rapid drying screeds used when laying bonded, unbonded or floating screeds prior to covering with vinyl sheet or other coverings. The fast drying properties allow screeds to be covered with moisture sensitive finishes as early as one day after application.

Drying times are determined by many factors including humidity, temperature and mixing. An effective damp proof membrane must be in place.

Drying Times—50mm screed (Relative Humidity at the surface)	24 hours	77%
	36 hours	75%
Drying Times—75mm screed (Relative Humidity at the surface)	24 hours	75%
	36 hours	< 75%
Physical Properties	Compressive Strength	
	1 day	25N/mm ²
	7 days	39N/mm ²
	28 days	44N/mm ²
	Flexural Strength	
	7 days	9.0N/mm ²
	28 days	12.0N/mm ²
	Tensile Strength	
	1 day	1.4N/mm ²
	7 days	3.4N/mm ²
28 days	3.6N/mm ²	

RonaScreed 1 Day Overlay Rapid Drying Screed

Cement replacement system for rapid drying screeds

Yield and Coverage	Packs required per m³ (approx) Packs required per m² @ 50mm Packs required per m² @ 75mm Approximate yield per mix	20.25 packs 1.01 packs 1.52 packs 0.048m³
Mix Design 1—Screed by weight (by volume)	RonaScreed 1 Day Overlay Rapid Dry Screed Medium grade sharp sand Water Minimum thickness	20kg (1) 80kg (3) add to achieve workability 25mm
Mix Design 2—Fine Concrete by weight (by volume)	RonaScreed 1 Day Overlay Rapid Dry Screed Medium grade sharp sand 10-5mm aggregate Water Minimum / maximum thickness	20kg (1) 40kg (1.5) 40kg (1.5) add to achieve workability 40mm / 100mm

Measuring Surface Dryness Laboratory tests for residual moisture indicate that RonaScreed 1 Day Overlay Rapid Dry Screed screeds will be dry enough to accept suitable vinyl and other coverings 24 hours after application. Good air movement is required to ensure low air humidity.

Instructions for Use It is essential that where no effective damp proof membrane exists RonaScreed DPM is first applied. Refer to RonaScreed DPM data sheet.

Priming

When laying a bonded screed (see Table 4) the surface must be mechanically prepared and tested to ensure it is suitable to restrain a bonded screed. Clean the substrate to remove dust and debris, damp with clean water and allow the water to soak in. Remove excess water and apply a bond coat of Ronacrete Rapid Primer well brushed into the damp surface. The screed must be laid on wet or tacky primer, dry primer must be vigorously scratched and reapplied.

Mixing

RonaScreed 1 Day Overlay Rapid Dry Screed must be machine mixed in a forced action mixer (e.g. CreteAngle pan mixer). Do not use a free fall mixer. Mix the dry components and when evenly dispersed add sufficient clean water for adequate compaction and surface finish and to ensure full hydration of the cement. Compaction of dry mixes will be poor and strength will be low.

Placing

RonaScreed 1 Day Overlay Rapid Dry Screed must be placed immediately after mixing. The screed must be compacted and closed with a float or trowel. Avoid overworking the surface.

Thicknesses above 50mm may be placed monolithically (wet on wet) in more than one layer to ensure full compaction. Each layer should be of approximately equal thickness. To ensure satisfactory adhesion the lower layer must be raked to

RonaScreed 1 Day Overlay Rapid Drying Screed

Cement replacement system for rapid drying screeds

Instructions for Use (continued)

provide a key for the next layer. If the workability of a layer is lost it must be mechanically if it has not been raked, before applying the next layer. Then apply a bond coat of Ronacrete Rapid Primer well brushed onto the surface and apply the next layer on to the wet/tacky primer.

Curing

Exposure of RonaScreed 1 Day Overlay Rapid Dry Screed to drying winds and direct sunlight should be avoided.

Packaging

RonaScreed 1 Day Overlay Rapid Dry Screed is supplied in 20kg sacks.

Shelf Life / Storage

RonaScreed 1 Day Overlay Rapid Dry Screed should be stored unopened between 5°C and 25°C in dry warehouse conditions and out of direct sunlight. In these conditions shelf life is approximately 9 months.

Health and Safety

Refer to Safety Data Sheet.


Site Attendance

When on site Ronacrete representatives are able, if asked, to give a general indication of the correct method of installing a Ronacrete product. It is important to bear in mind that Ronacrete Ltd is a manufacturer and not an application contractor and it is therefore the responsibility of the contractor and his employer to ensure he is aware of and implements the correct practices and procedures to ensure the correct installation of the product and that liability for its correct installation lies with the contractor and not with Ronacrete Ltd.



RonaScreed 1 Day Overlay Rapid Drying Screed

Cement replacement system for rapid drying screeds


Ronacrete Ltd, Flex Meadow, Harlow Essex, CM19 5TD, UK
13
BS EN 13813 Floor Screed
Product: RonaScreed 1 Day Overlay Rapid Drying Screed Reaction to Fire: A2-s1,d0 Release of Corrosive Substances: None Capillary Water Absorption: < 0.40kg / m² . min0.5 Compressive Strength: ≥ 40 Flexural Strength: ≥ F4 Wear Resistance BCA method: AR1 Dampness Test (headspace): 75% RH at 20C at 1 day Release of Dangerous Substances: Refer to Safety Data Sheet

The information detailed in this leaflet is liable to modification from time to time in the light of experience and of normal product application, and before using, customers are advised to check with Ronacrete Ltd, quoting the reference number, that they possess the latest issue. Any person or company using the product without first making further enquiries as to the suitability of the product for the intended use does so at his own risk, and Ronacrete Ltd can accept no responsibility for the performance of the product, or for any loss or damage arising out of such use.