


Flowseal EPW (0.12 mm dry film thickness)

A coloured, water based hygienic floor seal for use in food process areas, kitchens, light industrial areas, storerooms, garages and areas of pedestrian and light traffic.



1 Prepared Substrate 2 Flowseal EPW



Easy to Apply:

Simple, easy application by brush or roller



Attractive:

Enhances the appearance of working environment.



Hygienic:

Provides a seamless finish that is easy to clean and maintain.



Low Odour:

Exhibits a low odour during application.

FIRE RESISTANCE	
EN 13501-1	B _{fl} -s1
TEMPERATURE RESISTANCE	
Tolerant up to 70°C (intermittent) or 50°C (sustained)	
WEAR RESISTANCE <small>Taber Abrader, H22 wheels, 1000 cycles, 1kg load</small>	
EN ISO 5470-1	Weight loss < 100 mg
WEAR RESISTANCE	
EN 13892-4	AR0.5 (≤ 50 μm)
CAPILLARY ABSORPTION & WATER PERMEABILITY	
EN 1062-3	0.005 kg/m ² × h ^{0.5}
VAPOUR PERMEABILITY	
ASTM:E96:90	20 g / m ² / mm / 24 hr
BOND STRENGTH	
EN 13892-8	B2.0 (≥ 2 MPa)
IMPACT RESISTANCE	
EN ISO 6272	IR4 (4 Nm)
SURFACE HARDNESS	
Koenig Hardness Test	182 secs.
SLIP RESISTANCE*	
EN 13036-4 (typical values for 4-S rubber slider)	Dry >40 low slip potential

SPEED OF CURE	10°C	20°C	30°C
Light Traffic	24 hrs	12 hrs	8 hrs
Full Traffic	36 hrs	24 hrs	16 hrs
Full Chemical Cure	14 days	7 days	5 days

The figures above are typical properties achieved in laboratory tests at 20°C and at 50% Relative Humidity.

Signal white 050	Silk Grey 217	Goosewing Grey 222	Mid Grey 280
Sand Beige 326	Pastel Blue 452	Tile Red 637	Pastel Green 740

The applied colours may differ from the examples shown.
For a full colour chart and samples, contact your local CPG office.

Model Specification

System	Flowseal EPW
Finish	Gloss or Matt
Thickness	0.12 mm dry film thickness

Preparatory work and application in accordance with manufacturer's instructions.

Products Included In This System

Flowseal EPW (density = 1.3 kg/l) 1 st coat: Flowseal EPW 0.15 kg/m ² * 2 nd coat: Flowseal EPW 0.1 kg/m ² * *Application and coverage rates are assisted by addition of water: <ul style="list-style-type: none">• 20% water by weight of the unit (A+B) must be added to the mixed product for first coats and priming.• 10% water by weight of the unit (A+B) must be added to the mixed product for subsequent coats.• Note: Once diluted, do not add further quantities of water.	} Typical values
---	------------------

Detailed application instructions are available upon request.

Substrate Requirements

Concrete or screed substrate should be a minimum of 25 N/mm², free from laitance, dust and other contamination. The substrate should be dry to 93% as per BS8203 (5.5% on Tramex scale) and free from rising damp and ground water pressure.

Installation Service

The installation should be carried out by a CPG approved contractor with a documented quality assurance scheme. Obtain details of our approved contractors by contacting our customer service team or enquiring via our website www.flowcrete.eu.

Aftercare, Cleaning & Maintenance

Clean regularly using a single or double headed rotary scrubber drier in conjunction with a mildly alkaline detergent.

*The slipperiness of flooring materials can change significantly due to the installation process, after short periods of use, due to inappropriate maintenance, longer-term wear and/or surface contaminants (wet or dry). Textured systems are recommended to meet slip resistance value requirements for wet conditions and/ or surface contaminants (wet or dry). Please contact our Technical Department for further details and specifications.

Tremco CPG's products are guaranteed against defective materials and manufacture and are sold subject to its standard Terms and Conditions of Sale, copies of which can be obtained on request. Any suggested practices or installation specifications for the composite floor or wall system (as opposed to individual product performance specifications) included in this communication (or any other) from Tremco CPG constitute potential options only and do not constitute nor replace professional advice in such regard. Tremco CPG recommends any customer seek independent advice from a qualified consultant prior to reaching any decision on design, installation or otherwise.

System Datasheet written for Tremco CPG. Please consult Technical Team in your own country region for specific details. [28/11/23, 01 UK]

Note

No resin system is totally colour fast and may change colour over time (exhibits a yellowing effect). Colour change depends on the UV light and heat levels present and hence the rate of change cannot be predicted. This is more noticeable in very light colours but does not compromise the product's physical or chemical resistance characteristics. We have endeavoured to adopt colours within our standard range which minimise this change.

Intensively coloured products (e.g. hair colourants, medical disinfectants etc.) and plasticizer migration (e.g. from rubber tyres) can lead to irreversible discolouration in the surface. Please contact our Technical Services Department for further advice.

Environmental Considerations

The finished system is assessed as nonhazardous to health and the environment. The long service life and seamless surface reduce the need for repairs, maintenance and cleaning.

Environmental and health considerations are controlled during manufacture and application of the products by Tremco CPG staff and fully trained and experienced contractors.

Important Notes

CPG products are guaranteed against defective materials and manufacture and are sold subject to our standard 'Warranty, Terms and Conditions of Sale', copies of which can be obtained on request. Warranty does not cover suitability, fit for purpose or any consequential or related damages. Please review warranty in detail before installing the products.